

Description

MB-AE 90 air-entraining admixture is for use in concrete mixtures. It meets the requirements of ASTM C 260, AASHTO M 154 and CRD-C 13.

Applications

Recommended for use in:

- Concrete exposed to cyclic freezing and thawing
- Production of high-quality normal or lightweight concrete (heavyweight concrete normally does not contain entrained air)

MB-AE™ 90**Air-Entraining Admixture****Features**

- Ready-to-use in the proper concentration for rapid, accurate dispensing

Benefits

- Improved resistance to damage from cyclic freezing and thawing
- Improved resistance to scaling from deicing salts
- Improved plasticity and workability
- Reduced permeability – increased watertightness
- Reduced segregation and bleeding

Performance Characteristics

Concrete durability research has established that the best protection for concrete from the adverse effects of freezing and thawing cycles and deicing salts results from: proper air content in the hardened concrete, a suitable air-void system in terms of bubble size and spacing, and adequate concrete strength, assuming the use of sound aggregates and proper mixing, transporting, placing, consolidation, finishing and curing techniques. MB-AE 90 admixture can be used to obtain adequate freeze-thaw durability in a properly proportioned concrete mixture, if standard industry practices are followed.

Air Content Determination: The total air content of normal weight concrete should be measured in strict accordance with ASTM C 231, "Standard Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method" or ASTM C 173/C 173M, "Standard Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method."

The air content of lightweight concrete should only be determined using the Volumetric Method. The air content should be verified by calculating the gravimetric air content in accordance with ASTM C 138/C 138M, "Standard Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete." If the total air content, as measured by the Pressure Method or Volumetric Method and as verified by the Gravimetric Method, deviates by more than 1-1/2%, the cause should be determined and corrected through equipment calibration or by whatever process is deemed necessary.

Guidelines for Use

Dosage: There is no standard dosage for MB-AE 90 admixture. The exact quantity of air-entraining admixture needed for a given air content of concrete varies because of differences in concrete-making materials and ambient conditions. Typical factors that might influence the amount of air entrained include: temperature, cementitious materials, sand gradation, sand-aggregate ratio, mixture proportions, slump, means of conveying and placement, consolidation and finishing technique.

Product Data: MB-AE™ 90

The amount of MB-AE 90 admixture used will depend upon the amount of entrained air required under actual job conditions. In a trial mixture, use 1/4 to 4 fl oz/cwt (16-260 mL/100 kg) of cementitious material. Measure the air content of the trial mixture, and, if needed, either increase or decrease the quantity of MB-AE 90 admixture to obtain the desired air content.

In mixtures containing water-reducing or set-control admixtures, the amount of MB-AE 90 admixture needed may be somewhat less than the amount required in plain concrete.

Due to possible changes in the factors that can affect the dosage of MB-AE 90 admixture, frequent air content checks should be made during the course of the work. Adjustments to the dosage should be based on the amount of entrained air required in the mixture at the point of placement.

If an unusually high or low dosage of MB-AE 90 admixture is required to obtain the desired air content, consult your BASF Construction Chemicals representative. In such cases, it may be necessary to determine that, in addition to a proper air content in the fresh concrete, a suitable air-void system is achieved in the hardened concrete.

Dispensing and Mixing: Add MB-AE 90 admixture to the concrete mixture using a dispenser designed for air-entraining admixtures, or add manually using a suitable measuring device that ensures accuracy within plus or minus 3% of the required amount.

For optimum, consistent performance, the air-entraining admixture should be dispensed on damp, fine aggregate. If the concrete mixture contains fine lightweight aggregate, field evaluations should be conducted to determine the best method to dispense the air-entraining admixture.

Precaution

In a 2005 publication from the Portland Cement Association (PCA R&D Serial No. 2789), it was reported that problematic air-void clustering that can potentially lead to above normal decreases in strength was found to coincide with late additions of water to air-entrained concretes. Late additions of water include the conventional practice of holding back water during batching for addition at the jobsite. Therefore, caution should be exercised with delayed additions of water to air-entrained concrete. Furthermore, an air content check should be performed after any post-batching addition to an air-entrained concrete mixture.

Product Notes

Corrosivity – Non-Chloride, Non-Corrosive: MB-AE 90 admixture will neither initiate nor promote corrosion of reinforcing and prestressing steel embedded in concrete, or of galvanized floor and roof systems. No calcium chloride or other chloride-based ingredients are used in the manufacture of this admixture.

Compatibility: MB-AE 90 admixture may be used in combination with any BASF Construction Chemicals admixture, unless stated otherwise on the data sheet for the other product. When used in conjunction with other admixtures, each admixture must be dispensed separately into the concrete mixture.

Storage and Handling

Storage Temperature: MB-AE 90 admixture should be stored and dispensed at 31 °F (-0.5 °C) or higher. Although freezing does not harm this product, precautions should be taken to protect it from freezing. If MB-AE 90 admixture freezes, thaw at 35 °F (2 °C) or above and completely reconstitute by mild mechanical agitation. **Do not use pressurized air for agitation.**

Shelf Life: MB-AE 90 admixture has a minimum shelf life of 18 months. Depending on storage conditions, the shelf life may be greater than stated. Please contact your BASF Construction Chemicals representative regarding suitability for use and dosage recommendations if the shelf life of MB-AE 90 admixture has been exceeded.

Safety: Chemical goggles and gloves are recommended when transferring or handling this material.

Packaging

MB-AE 90 admixture is supplied in 55 gal (208 L) drums, 275 gal (1040 L) totes and by bulk delivery.

Related Documents

Material Safety Data Sheets: MB-AE 90 admixture.

Additional Information

For additional information on MB-AE 90 admixture, or its use in developing a concrete mixture with special performance characteristics, contact your BASF Construction Chemicals representative.

The Admixture Systems business of BASF Construction Chemicals is a leading provider of innovative additives for specialty concrete used in the ready mix, precast, manufactured concrete products, underground construction and paving markets throughout the NAFTA region. The Company's respected Master Builders brand products are used to improve the placing, pumping, finishing, appearance and performance characteristics of concrete.

BASF Construction Chemicals, LLC
Admixture Systems

www.masterbuilders.com

United States 23700 Chagrin Boulevard, Cleveland, Ohio 44122-5544 ■ Tel: 800 628-9990 ■ Fax: 216 839-8821
Canada 1800 Clark Boulevard, Brampton, Ontario L6T 4M7 ■ Tel: 800 387-5862 ■ Fax: 905 792-0651

™BASF Construction Chemicals, LLC

© BASF Construction Chemicals, LLC 2007 ■ Printed in USA ■ 03/07 ■ LIT # 1017027



**Master
Builders**



The Chemical Company

April 22, 2007

Kearney Concrete Company
2001 Avenue C
Kearney, Nebraska, 68847

Attention: Kyle Poff
Project:
Project location:

Certificate of Conformance
Pave-Air™ 90
BASF Construction Chemicals, LLC* Air-Entraining Admixture for Concrete
(*Previously doing business as BASF Admixtures, Inc. and prior to that as Degussa Admixtures, Inc. and Master Builders, Inc.)

I, Richard Hubbard, Technical Specialist for BASF Construction Chemicals, LLC, Cleveland, Ohio, certify:

That Pave-Air™ 90 is a BASF Construction Chemicals, LLC air-entraining admixture for concrete; and

That no calcium chloride or chloride based ingredient is used in the manufacture of Pave-Air™ 90; and

That Pave-Air™ 90, based on the chlorides originating from all the ingredients used in its manufacture, contributes less than 0.000068 percent (0.68 ppm) chloride ions by weight of the cement when used at the rate of 65 ml per 100 kg (1 fluid ounce per 100 pounds) of cement; and

That Pave-Air™ 90 meets the requirements of ASTM C 260, Corps of Engineers' CRD-C 13, and AASHTO M154, the Standard Specifications for Air-Entraining Admixtures for Concrete.

Richard Hubbard
Technical Specialist
BASF Construction Chemicals, LLC

BASF Construction Chemicals, LLC
23700 Chagrin Boulevard
Cleveland, OH 44122
216 839-7500 ph
www.basf-admixtures.com

**Master
Builders**
Admixture Solutions



The Chemical Company

September 6, 2007

KEARNEY CONCRETE CO
2001 AVE. C
Kearney, Nebraska 68847

Attention: Kyle Poff
Project: Bridge resurfacing/silica pfume concrete
Project location: Shelton, Ne

Certificate of Conformance
Pave-Air™ 90
BASF Construction Chemicals, LLC* Air-Entraining Admixture for Concrete
(*Previously doing business as BASF Admixtures, Inc. and prior to that as Degussa Admixtures, Inc. and Master Builders, Inc.)

I, Richard Hubbard, Technical Specialist for BASF Construction Chemicals, LLC, Cleveland, Ohio, certify:

That Pave-Air™ 90 is a BASF Construction Chemicals, LLC air-entraining admixture for concrete; and

That no calcium chloride or chloride based ingredient is used in the manufacture of Pave-Air™ 90; and

That Pave-Air™ 90, based on the chlorides originating from all the ingredients used in its manufacture, contributes less than 0.000068 percent (0.68 ppm) chloride ions by weight of the cement when used at the rate of 65 ml per 100 kg (1 fluid ounce per 100 pounds) of cement; and

That Pave-Air™ 90 meets the requirements of ASTM C 260, Corps of Engineers' CRD-C 13, and AASHTO M154, the Standard Specifications for Air-Entraining Admixtures for Concrete.

Richard Hubbard
Technical Specialist
BASF Construction Chemicals, LLC

BASF Construction Chemicals, LLC
23700 Chagrin Boulevard
Cleveland, OH 44122
216 839-7500 ph
www.basf-admixtures.com

**Master
Builders**
Admixture Solutions